



Technical data sheet

Material: **PPc brown MFI 20–30**

Reccomended processing method: **Injection molding**

This a general recommendation of use for applications where no recycled material has been used yet. From the beginning we recommend to mix it with plastics that have been previously used and gradually add the amount up to 100%.

| Declared parameters | | | |
|--|---------------------|-------------------------|----------------|
| PARAMETER | UNIT | TESTING METHOD | TYPICAL VALUES |
| Melt flow index at 230°C and 2,16 kg | g / 10 min. | ISO 1133 | 20 – 30 |
| Bulk density at 23°C | g/ cm ³ | ISO 1183 | 0,97 – 1,06 |
| Tensile strength at 23°C | MPa | ISO 527 | 20 – 30 |
| Elasticity modulus E at 23°C | MPa | ISO 527 | 850 – 1100 |
| Elongation at tensile strength point at 23°C | % | ISO 527 | 7 – 10 |
| Elongation at break at 23°C | % | ISO 527 | 10 – 60 |
| Charpy notched impact strength | kJ / m ² | ISO 179 (notch V) +23°C | 2,9 – 4,5 |
| Charpy notched impact strength | kJ / m ² | ISO 179 (notch V) -20°C | 2,1 – 3,2 |
| Ash content at 600°C, 30 min. | % | ISO 3451 | 5 – 15 |

Data from the table above are representing typical range of values of each parameter. These data are only informative and should help to producers by choice of the right application. Producers can't expect complete possibility of replacement of virgin plastics by recycled plastics with same productivity and/or scrap rate. Only the very deviation from the range of values therefore can not be used as a reason for claims and/or requirements of price reduction.